




COMPOSIÇÃO: INTERIOR EM BORRACHA SINTÉTICA, SEGUIDO POR QUATRO TRANÇAS DE AÇO E REFORÇADO COM OUTRA CAMADA EXTERNA DE BORRACHA.

TEMPERATURA:

-40° +100°

NORMAS: EN 856 4SH, ISO 1307

TUBO R9/4SH



INTERIOR



EXTERIOR



MAX. PRESSÃO DE TRABALHO



PRESSÃO DE ROTURA



ÂNGULO DE TRABALHO



PESO

CÓDIGO	NOMINAL	mm	mm	bar	psi	bar	psi	mm	g/m
0303000005	3/4"	19	32	420	6090	1680	24360	280	1465
0303000006	1"	25,4	38,4	380	5510	1520	22040	340	2035
0303000007	1 1/4"	31,8	45,2	350	5075	1400	20300	460	2385
0303000008	1 1/2"	38,1	53	290	4205	1160	16820	560	3185
0303000009	2"	50,8	67,6	250	3625	1000	14500	700	4365

